



ANALİZ SERTİFİKASI/CERTIFICATE ANALYSIS

ÜRÜN ADI/PRODUCT NAME	GENERAL
ÜRÜN KODU/PRODUCT CODE	GENERAL
ÜRÜN TİPİ/PRODUCT TYPE	POLYESTER

ÖN İŞLEM/PRE-TREATMENT	IRON PHOSPHATE
KÜRLENME/CURING	200 °C-10 min.
FİLM KALINLIĞI/FILM THICKNESS	80 µ ± 5

TOZ BOYA ÖZELLİKLERİ/POWDER PROPERTIES

KONTROLLER/CONTROLS	STANDART	BİRİM	BATCH
RENK/COLOUR X-RITE		$\Delta E < 1$	0,35
PARLAKLIK/GLOSS 60°	Test ISO 2813	90°	NON
YOĞUNLUK/DENSITY	Test ISO 8130-3	gr/m ³	1,6
AKIŞKANLIK/FLOWMETRE	Test ISO8130-5	120-160	136

LAZER ANALİZİ/LAZER ANALYZER	PARTİ
>99 µ%	3,50
<72 µ%	18,50
<31 µ%	71,00
<10 µ%	7,00

MEKANİK TESTLER/MECHANICALS TEST

KONTROLLER/CONTROLS	STANDART	BİRİM	BATCH
DARBE TESTİ/IMPACT TEST	Test ISO 6272	60-100 kg/cm	80
FİLM SERTLİĞİ/FILM HARDNESS BUCHHOLZ	Test ISO 2815	>=8	NON
KONİK BÜKME/CONICAL MANDREL	Test ISO 6860	mm	8,5
YAPIŞMA/CROSS-CUT	Test ISO 2409	gt	gt0

UYGULAMA ŞARTLARI/APPLICATION CONDITIONS

KÜRLENME/CURING	200 °C-10 min.
FİLM KALINLIĞI/FILM THICKNESS	80 µ ± 5
UYGULAMA METODU/APPLICATION METHOD	CORONA
GERİ DÖNÜŞÜM/POWDER RECYLING	max.%20

STOKLAMA ŞARTLARI/STORAGE CONDITIONS

- KURU YERDE DİREKT GÜNEŞ IŞIĞI GÖRMEYECEK/DRY PLACE DON'T DIRECT SUNLIGHT.

STOKLAMA ORTAM SICAKLIĞI/STORAGE PLACE TEMPERATURE

- < 25°C MAX.SICAKLIK ALTINDA/ < 25°C MAX.UNDER TEMPERATURE

RAF ÖMRÜ 12 AY/SHELF LIFE 12 MONTHS